

SPECIFICATION PRODUCT CODE - 300 - DUPLEX

Sample Code	Description	Substance (GSM)	Caliper	Bulk	Stiffness			Moisture %
					MD	CD	GM	
300	White Back	285	308	1.08	80	35	53.00	6.5-7.0
300	White Back	296/300	324	1.08	90	40	60.00	6.5-7.0
300	White Back	330	363	1.10	115	45	72.00	7.0-8.0
300	White Back	350	389	1.11	130	50	80.60	7.0-8.0
300	White Back	370	414	1.12	160	65	102.00	7.0-8.0
300	White Back	400	448	1.12	190	80	123.20	7.0-8.0
300	Grey Back	230	271	1.18	45	18	28.00	6.0-6.5
300	Grey Back	250	295	1.18	65	25	40.30	6.5-7.0
300	Grey Back	285	336	1.18	90	36	57.00	6.5-7.0
300	Grey Back	296/300	360	1.20	105	42	66.40	6.5-7.0
300	Grey Back	330	399	1.21	135	55	86.00	7.5-7.8
300	Grey Back	350	427	1.22	150	60	95.00	7.5-7.8
300	Grey Back	370	451	1.22	170	68	107.50	7.5-7.8
300	Grey Back	400	488	1.22	215	90	139.00	7.5-7.8
300	Grey Back	450	549	1.22	240	110	162.00	7.8-8.0

SPECIFICATION PRODUCT CODE - 130 - DUPLEX

Sample Code	Description	Substance (GSM)	Caliper	Bulk	Stiffness			Moisture %
					MD	CD	GM	
130	White Back	250	283	1.13	63	27	41.20	6.5
130	White Back	260	294	1.13	65	28	42.60	6.5
130	White Back	285	325	1.14	93	41	61.70	6.5
130	White Back	296	344	1.16	97	42	63.80	7.0
130	White Back	320	372	1.16	135	57	87.70	7.0
130	White Back	350	403	1.16	145	64	96.30	7.0
130	White Back	360	418	1.16	150	65	98.70	7.0
130	White Back	370	433	1.17	180	77	117.70	7.0
130	White Back	400	472	1.18	230	96	148.60	7.5
130	White Back	450	544	1.21	330	135	211.10	8.0
130	Grey Back	250	293	1.17	72	31	47.20	6.5
130	Grey Back	260	307	1.18	80	34	52.10	6.5
130	Grey Back	285	342	1.20	105	45	68.70	6.5
130	Grey Back	296	356	1.20	115	50	75.80	7.0
130	Grey Back	320	384	1.20	138	60	90.90	7.0
130	Grey Back	330	396	1.20	147	61	94.70	7.0
130	Grey Back	340	411	1.20	158	65	101.30	7.0
130	Grey Back	350	424	1.21	170	70	109.10	7.0
130	Grey Back	360	436	1.21	180	74	115.40	7.0
130	Grey Back	370	448	1.21	188	80	122.60	7.0
130	Grey Back	400	488	1.22	240	100	154.90	7.5
130	Grey Back	450	554	1.23	320	135	207.80	8.0

Contact Us:

Ph: +91 9999535321, +91 9717538855 | Email: Export@knammarketing.com | Website: www.knammarketing.com

SPECIFICATION PRODUCT CODE - 130 - DUPLEX

Colour Range : RED, BLUE, YELLOW, GOLDEN YELLOW & GREEN								
Sample Code	Description	Substance (GSM)	Caliper	Bulk	Stiffness			Moisture %
					MD	CD	GM	
130	Coloured file board (CFB)	245	314	1.28	80	33		6.0
130	Coloured file board (CFB)	310	397	1.28	150	62		6.5
130	Coloured file board (CFB)	395/400	520	1.3	300	125		7.0
130	Coloured file board (CFB)	465/475	628	1.32	420	175		7.5
130	Coloured file board (CFB)	540/550	727	1.32	530	220		8.0

SPECIFICATION PRODUCT CODE - 800 - DUPLEX

Sample Code	Description	Substance (GSM)	Caliper	Bulk	Stiffness			Moisture %
					MD	CD	GM	
800		230	292	1.27	115	56	79.00	6.5-8.0
800		250	318	1.27	160	75	109.00	6.5-8.0
800		260	33	1.28	177	80	119.00	6.5-8.0
800		270	346	1.28	195	86	129.00	6.5-8.0
800		280	361	1.29	216	95	143.00	6.5-8.0
800		290	380	1.31	240	110	162.00	6.5-8.0
800		300	393	1.31	260	120	177.00	6.5-8.0
800		320	422	1.32	320	145	215.00	7.0-8.5
800		330	439	1.33	350	160	236.00	7.0-8.5
800		340	452	1.33	30	170	257.00	7.0-8.5
800		350	466	1.33	418	183	277.00	7.0-8.5
800		360	482	1.34	440	195	293.00	7.0-8.5
800		370	496	1.34	480	210	317.00	7.0-8.5
800		380	513	1.35	508	220	334.00	7.0-8.5
800		390	527	1.35	533	230	350.00	7.0-8.5
800		400	540	1.35	572	247	376.00	7.0-8.5
800		420	571	1.36	690	300	455.00	
800		430	585	1.36	720	312	474.00	
800		450	612	1.36	780	335	511.00	

Contact Us:

Ph: +91 9999535321, +91 9717538855 | Email: Export@knammmarketing.com | Website: www.knammarketing.com