

## SPECIFICATION -EOCC PULP

Specification	Testing Result
GSM	180
Bursting Factor	11.8
COBB 60 sec Top/bottom	300
	320
Tear Factor (MD)	-
Tear Factor (CD)	-
Moisture	8%-9%
RCT/CD (KGF)	12.2
RCT/CD (KN/M)	0.79
Thickness	230-240
Bulk	1.1
Freeness	20-22
Range of GSM	180-250 gsm
Reel width	1300 mm
Dia	1100 mm

**Contact Us:**