

SPECIFICATION PRODUCT CODE - 900 - KRAFT

PRODUCT CODE	GSM	BF	BURSTING STRENGTH	RCT (CD)	THICKNESS	COBB (60 sec)	Moisture %
90018	100	18	2.0	0.72	120	30	6.75
	120	18	2.3	0.85	145	30	6.75
	140	18	2.5	1.10	175	28	7.00
	150	18	2.7	1.30	180	28	7.00
	170	18	3.1	1.42	220	25	7.00
	180	18	3.2	1.50	240	25	7.00
	200	18	3.5	1.82	260	25	7.00
	220	18	3.9	2.10	280	25	7.20
90020	120	20	2.4	1.70	135	30	7.00
	140	20	2.9	1.80	150	30	7.00
	150	20	3.1	1.90	170	30	7.00
	170	20	3.4	2.20	230	30	6.80
	180	20	3.6	2.30	245	28	7.00
	200	20	4.1	2.50	265	28	7.10
	220	20	4.5	2.70	285	28	7.20
90022	130	22	2.9	1.80	140	28	7.00
	140	22	3.1	1.95	155	28	7.00
	150	22	3.4	2.10	175	28	7.00
	170	22	3.8	2.35	240	28	7.00
	180	22	4.0	2.40	252	28	7.00
	200	22	4.5	2.65	270	30	7.10
	220	22	4.9	2.75	292	30	7.20
90024	130	24	3.2	1.80	155	35	7.00
	150	24	3.7	2.00	190	35	7.00
	170	24	4.2	2.30	240	30	7.00
	180	24	4.4	2.50	250	38	7.00
	200	24	4.9	2.70	280	35	7.00
	220	24	5.3	2.80	300	35	7.20
90028	140	28	4.0	1.60	170	45	7.00
	150	28	4.3	1.70	180	45	7.00
	170	28	4.8	2.00	240	45	7.00
	180	28	5.1	2.10	250	48	7.00
	200	28	5.6	2.30	270	48	7.20
	220	28	6.2	2.50	290	48	7.20
90032	140	32	4.5	1.80	180	45	7.00
	150	32	4.8	1.90	185	45	7.00
	170	32	5.5	2.10	245	45	7.00
	180	32	5.8	2.20	255	48	7.10
	200	32	6.4	2.50	275	48	7.20
	220	32	7.1	2.60	300	50	7.20
90035	140	35	4.9	2.00	185	45	7.00
	150	35	5.3	2.10	190	45	7.00
	170	35	6.0	2.30	250	45	7.00
	180	35	6.3	2.50	260	48	7.10
	200	35	7.0	2.70	280	48	7.10
	220	35	7.8	2.80	305	50	7.20

Contact Us:
Ph: +91 9999535321, +91 9717538855 | **Email:** Export@knammarketing.com | **Website:** www.knammarketing.com